

Laboratory Chemical Report

Hanson Cement
 Ketton
 Stamford
 PE9 3SX
 Tel: 0330 123 2074
 Fax: 01780 727008

Composition of Ketton Rapid Hardening PC, BS EN 197-1:2011, CEM I 52,5R

Manufactured at Ketton.

Chemical analysis for week ending 23 Jul 2017 (Week No. 29)

Compound	%
SiO ₂	18.76
Al ₂ O ₃	4.41
Fe ₂ O ₃	2.90
CaO	62.38
MgO	1.12
SO ₃	3.30
K ₂ O	0.70
Na ₂ O	0.22
Cl	0.06
Loss on Ignition	4.04
Not Detected	2.11
Total	100.00

	%
Insol Residue	0.57
Free CaO	0.7
Certified Average Alkali Na ₂ O (Equiv)	0.68
LSF (x 100)	100.5

Clinker compounds by Rietveld analysis	
C ₃ S	65.1
C ₂ S	11.5
C ₃ A	5.7
C ₄ AF	8.3

For and on behalf of
 HANSON CEMENT



National Technical Manager
 Hanson Cement

The Company has used all reasonable care to ensure the information herein contained is accurate but no liability can be accepted for any loss or damage arising from any inaccuracy, whether due to their negligence or otherwise.