



Castle Cement Ltd T/A
Hanson Cement, Hanson House, 14 Castle Hill,
Maidenhead, Berkshire, SL6 4JJ
Ribblesdale Works
1333-CPR-00127



Cement Test Report

Hanson Cement
Ketton
Stamford
PE9 3SX
Tel: 0330 123 2074
Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of
Ribblesdale PC, BS EN 197-1:2011 - CEM I 52,5N

Dispatched from Ribblesdale during week ending
and during week ending

15-Jan-23 (Week No. 2023-2)
25-Dec-22 (Week No. 2022-51) for 28 day results

Date	Fineness Specific Surface (m ² /kg)	Setting Time Initial (mins)	Soundness Expansion (mm)	Compressive Strength			Chloride %	Alkali	
				40mm x 40mm x 160mm Mortar prisms				Certified Average Alkali % Na ₂ O eq	Standard Deviation
				2 Days (N/mm ²)	7 Days (N/mm ²)	28 Days (N/mm ²)			
09-Jan-23	430	140	1	34.0	46.0		0.06	0.67	0.03
10-Jan-23	410	135	1	35.0	49.0		0.06	0.67	0.03
11-Jan-23	415	135	1	36.0	49.5		0.06	0.66	0.03
12-Jan-23	395	130	0	35.5	50.0		0.06	0.66	0.03
13-Jan-23	420	135	1	35.0	47.5		0.06	0.66	0.03
Average	415	135	1	35.0	48.5		0.06		0.03
19-Dec-22	395	145	1	35.0	48.0	61.0	0.06	0.67	0.03
20-Dec-22	395	145	1	35.0	50.0	61.0	0.06	0.67	0.03
21-Dec-22	405	150	0	34.5	49.5	61.5	0.06	0.67	0.03
Average	400	145	1	35.0	49.0	61.0	0.06		0.03

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Chloride content (%) = 0.07 (Max)

For and on behalf of
HANSON CEMENT

Dr Nina Cardinal, Dipl.Ing., CEng, MiMMM
National Technical Manager
Hanson Cement

Hanson Cement has used all reasonable care to ensure the
information herein contained is accurate but to the extent
permitted in law, no liability can be accepted by Hanson
Cement for any loss, damage, cost or expense arising from
any inaccuracy, whether due to negligence or otherwise.