



Castle Cement Ltd T/A
 Hanson Cement, Hanson House, 14 Castle Hill,
 Maidenhead, Berkshire, SL6 4JJ
 Ketton Works
 1333-CPR-00254



Cement Test Report

Hanson Cement
 Ketton
 Stamford
 PE9 3SX
 Tel: 0330 123 2074
 Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of
 Ketton PLC 52,5N, BS EN 197-1:2011 - CEM II/A-LL 52,5N

Dispatched from Ketton during week ending
 and during week ending

22-Jan-23 (Week No. 2023-3)
 01-Jan-23 (Week No. 2022-52) for 28 day results

Date	Fineness Specific Surface (m ² /kg)	Setting Time Initial (mins)	Soundness Expansion (mm)	Compressive Strength			Chloride %	Alkali	
				40mm x 40mm x 160mm Mortar prisms				Certified Average Alkali % Na ₂ O eq	Standard Deviation
				2 Days (N/mm ²)	7 Days (N/mm ²)	28 Days (N/mm ²)			
16-Jan-23	485	195	0	32.0	50.0		0.05	0.64	0.02
18-Jan-23	485	200	0	32.5	49.5		0.05	0.64	0.03
Average	485	200	0	32.5	50.0		0.05		0.02
Average	#DIV/0!	#DIV/0!	#DIV/0!	#DIV/0!		#DIV/0!	#DIV/0!		#DIV/0!

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Chloride content (%) = 0.07 (Max)

For and on behalf of
 HANSON CEMENT

Dr Nina Cardinal, Dipl.Ing., CEng, MiMMM
 National Technical Manager
 Hanson Cement

Hanson Cement has used all reasonable care to ensure the
 information herein contained is accurate but to the extent
 permitted in law, no liability can be accepted by Hanson
 Cement for any loss, damage, cost or expense arising from
 any inaccuracy, whether due to negligence or otherwise.