



Castle Cement Ltd T/A
Hanson Cement, Hanson House, 14 Castle Hill,
Maidenhead, Berkshire, SL6 4JJ
Ketton Works
1333-CPR-00135



Cement Test Report

Hanson Cement
Ketton
Stamford
PE9 3SX
Tel: 01330 123 2074
Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of
Ketton CGPC, BS EN 197-1:2011 - CEM I 42,5N
Dispatched from Ketton during week ending
and during week ending

10-Jul-22 (Week No. 2022-27)
19-Jun-22 (Week No. 2022-24) for 28 day results

Date	Fineness Specific Surface (m ² /kg)	Setting Time Initial (mins)	Soundness Expansion (mm)	Compressive Strength			Chloride %	Alkali	
				40mm x 40mm x 160mm Mortar prisms				Certified Average Alkali % Na ₂ O eq	Standard Deviation
				2 Days (N/mm ²)	7 Days (N/mm ²)	28 Days (N/mm ²)			
04-Jul-22	330	170	1	23.5	39.0		0.04	0.68	0.07
06-Jul-22	325	175	2	25.0	39.5		0.04	0.68	0.07
Average	330	175	1	24.5	39.5		0.04		0.07
13-Jun-22	320	195	1	24.5	39.0	53.5	0.04	0.70	0.06
15-Jun-22	325	155	1	23.0	38.5	55.5	0.04	0.70	0.06
Average	325	175	1	24.0	39.0	54.5	0.04		0.06

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Chloride content (%) = 0.07 (Max)

For and on behalf of
HANSON CEMENT

Dr Nina Cardinal, Dipl.Ing., CEng, MiMMM
National Technical Manager
Hanson Cement

Hanson Cement has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Hanson Cement for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.