Castle Cement Ltd T/A
Hanson Cement, Hanson House, 14 Castle Hill,
Maidenhead, Berkshire, SL6 4JJ
Ribblesdale Works
1333-CPR-00127





## **Cement Test Report**

Hanson Cement Ketton Stamford PE9 3SX

Tel: 0330 123 2074 Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of

Ribblesdale PC, BS EN 197-1:2011 - CEM I 52,5N

Dispatched from Ribblesdale during week ending

and during week ending

10-Jul-22 (Week No. 2022-27 )

19-Jun-22 (Week No. 2022-24 ) for 28 day results

Date	Fineness	Setting Time	Soundness	Compressive Strength			Chloride	Alkali	
	Specific	Initial	Expansion	40mm x 40i	40mm x 40mm x 160mm Mortar prisms			Certified Average Alkali	Standard
	Surface (m²/kg)	(mins)	(mm)	2 Days	7 Days	28 Days	%	% Na₂O eq	Deviation
				$(N/mm^2)$	(N/mm <sup>2</sup> )	(N/mm <sup>2</sup> )			
04-Jul-22	400	165	1	34.5	48.5		0.07	0.71	0.02
05-Jul-22	400	165	1	34.0	48.5		0.07	0.71	0.02
06-Jul-22	400	165	1	35.0	49.0		0.07	0.71	0.02
07-Jul-22	405	160	1	33.5	46.0		0.07	0.70	0.02
08-Jul-22	410	145	1	34.0	49.0		0.07	0.71	0.02
Average	405	160	1	34.0	48.0		0.07		0.02
13-Jun-22	410	160	0	36.5	50.0	62.0	0.06	0.69	0.04
14-Jun-22	415	150	0	35.0	50.0	62.5	0.06	0.69	0.04
15-Jun-22	410	150	1	33.5	48.0	60.0	0.06	0.69	0.04
16-Jun-22	390	160	1	35.5	48.5	61.0	0.06	0.69	0.04
17-Jun-22	390	165	0	33.5	48.0	61.0	0.06	0.69	0.04
Average	405	155	1	35.0	49.0	61.5	0.06		0.04

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max) Declared Chloride content (%) = 0.07 (Max)

For and on behalf of HANSON CEMENT

10 Cerdial

Dr Nina Cardinal, Dipl.Ing., CEng, MiMMM

National Technical Manager

Hanson Cement

Hanson Cement has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Hanson Cement for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.