



Regen Ground Granulated Blastfurnace Slag Produced at	Teesside SF
Sample Period	August 2021

The sample was tested following the methods given in BS EN 196-2. Additions and modifications have been mande in accordance with the Hanson Cement Testing Manual.

Chemical Composition %	
SiO2	35.90
AI2O3	14.20
Fe2O3	0.99
CaO	41.13
MgO	6.66
MnO	0.33
Mn2O3 Calc	0.36
TiO2	0.45
St	0.68
\$2-	0.63
SO3	0.13
L.O.I.	1.38
I.R.	0.32
С	0.21
CI	0.01
Glass content - XRD	
Relative Density g/cm2	2.88

The majority of the feed is manufactured by granulation, though on occasion a proportion of it may be by pelletisation.

The Regen GGBS contained no additional materials other than those permitted. The above results and other tests demonstrate the conformity of the material sold during the month to the requirements of EN 15167-1.

Hanson Cement has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Hanson Cement for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.

Signed:

b Cerdial



Dr Nina Cardinal, Dipl.Ing., CEng, MiMMM National Technical Manager