



Castle Cement Ltd T/A  
 Hanson Cement, Hanson House, 14 Castle Hill,  
 Maidenhead, Berkshire, SL6 4JJ  
 Padeswood Works  
 1333-CPR-00255



## Cement Test Report

Hanson Cement  
 Ketton  
 Stamford  
 PE9 3SX  
 Tel: 01330 123 2074  
 Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of  
 Padeswood PLC 52,5N, BS EN 197-1:2011 - CEM II/A-LL 52,5N

Dispatched from Padeswood during week ending 15-May-22 (Week No. 2022-19 )  
 and during week ending 24-Apr-22 (Week No. 2022-16 ) for 28 day results

Date	Fineness Specific Surface (m <sup>2</sup> /kg)	Setting Time Initial (mins)	Soundness Expansion (mm)	Compressive Strength			Chloride %	Alkali	
				40mm x 40mm x 160mm Mortar prisms				Certified Average Alkali % Na <sub>2</sub> O eq	Standard Deviation
				2 Days (N/mm <sup>2</sup> )	7 Days (N/mm <sup>2</sup> )	28 Days (N/mm <sup>2</sup> )			
12-May-22	590	175	1	37.0	49.5		0.05	0.60	0.05
13-May-22	565	170	1	37.0	50.5		0.05	0.60	0.05
Average	580	175	1	37.0	50.0		0.05		0.05
Average	#DIV/0!	#DIV/0!	#DIV/0!	#DIV/0!		#DIV/0!	#DIV/0!		#DIV/0!

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Chloride content (%) = 0.07 (Max)

For and on behalf of  
 HANSON CEMENT

Dr Nina Cardinal, Dipl.Ing., CEng, MiMMM  
 National Technical Manager  
 Hanson Cement

Hanson Cement has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Hanson Cement for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.